



Environmental Product **Declaration**



In accordance with ISO 14025 and EN 15804:2012+A2:2019

Bare Spiral Welded Steel Pipes

from

MAZLUM STEEL PIPES



PROGRAMME The International EPD[®] System *www.environdec.com*

EPD Turkey www.edpturkey.org PROGRAMME OPERATOR EPD International AB & EPD Turkey

EPD REGISTIRATION NUMBER S-P-04477 **PUBLICATION DATE** 2021-09-03

VALID UNTIL 2026-09-02

An EPD should provide current information and may be updated if conditions change. The stated validity is therefore subject to the continued registration and publication at: **environdec.com**



Programme Information

> Programme Information

Programme	The International EPD [®] System
Address	EPD International AB Box 21060 SE-100 31 Stockholm, Sweeden
Website	www.environdec.com
E-mail	info@environdec.com

Information about verification and reference PCR:

CEN standard EN 15804 serves as the Core Product Category Rules (PCR)							
Product category rules (PCR) PCR 2019:14 Construction products (EN 15804:A2) Version 1.1							
PCR review was conducted by The Technical Committee of the International EPD® System. See www.environdec.com/TC for a list of members. Review chair: Claudia A. Peña, University of Concepción, Chile. The review panel may be contacted via the Secretariat www.environdec.com/contact.							
Independent third-party verification of the declaration and data, according to ISO 14025:2006:							
Third party verifierApproved byVladimír Kočí, PhDInternational EPD System Technical Commiee, supported by the Secretariat							
Procedure for follow-up of data during EPD validity involes third party verifier:							
Yes Vo							
» LCA Study & EPD Design Conducted by							
Semtrio Sustainability Consulting BUDOTEK Teknopark, No 4/21 Umraniye / Istanbul Turkey www.semtrio.com							

Mazlum Steel Pipes. has the sole ownership, liability, and responsibility for the EPD.

EPDs within the same product category but from different programmes may not be comparable.EPDs of construction products may not be comparable if they do not comply with EN 15804. For further information about comparability, see EN 15804 and ISO 14025.

Company Information

> Owner of the EPD

Mazlum Mangtay Boru Sondajcılık İnş. Tarım Ürünleri San. Tic. A.Ş. Adana Hacı Sabancı OSB İstiklal Caddesi No: 10 Sarıçam - Adana / Turkey **Contact** Güney Demir guney.demir@mazlumboru.com.tr

Mazlum Steel Pipes, which has the highest standard in the sector with its capacity to make polyethylene coating between 219 mm and 3600 mm diameter, fully complies with the European Union and World Environmental Protection standards.

Mazlum Steel Pipes started as a Water Drilling Company in the 1950's by Mr. Mazlum Mangtay who was one of the most influental people in this sector. After struggling to procure reliable pipes for drilling, the decision was made in 1987 to start producing our own drilling pipes.

After securing a reasonable Market share in the steel pipes sector, the Management decided to implement new technologies and started producing spirally submerged double arc welded steel pipes, becoming one of the Market leaders in this sector. In June 2010 the company moved its factory from 12.000 m² facility to a new one in Adana Organize Industrial Area just outside the city. The new **36.000 m² facility** includes an area dedicated for polyethylene coating along with all other necessary production stations.

Moreover the addition of a third line machine has made it one of Turkey's most sought-after companies. The new factory has almost doubled the company's production with an **annual capacity now reaching 80.000 tons**, meeting Turkish and international standards.

Mazlum Mangtay, Co. started out as a local family company in Adana and has grown to become one of most established corporations in Turkey and abroad while being *enterprising, innovative and always making customer satisfaction its goal*.

Mazlum Steel Pipes, proving its reliability at Turkey and abroad by always offering the best products as one of the leading companies in the sector with its continuous investments over the years, continues to strengthen, grow, and add value to our country by exporting 60% of its production to more than 40 countries.







Ürünleri San. Tic. A.Ş. Adana Hacı Sabancı OSB İstiklal Caddesi No: 10 Sarıçam - Adana / Turkey



> Production

6

Spiral welded steel pipes are used in many different fields; water distribution lines, natural gas distribution lines, steel structures, industrial pipe networks, compressed air lines, transportation of high temperature water, oil pipelines, foundation piles, drilling wells, hydroelectric power plant projects, shipyard and port piles.

Hot rolled coils supplied from Turkey and abroad, after being formed by cold forming in spiral form, are welded internally and externally as single or tandem with the latest technology submerged arc welding method. Before forming, welding mouths are opened in different sizes depending on the thickness of the band edges automatically. This process not only ensures the welding quality and penetration, but also eliminates the band edge defects. Dimensional and visual controls are carried out continuously during forming and submerged arc welding processes. The online ultrasonic device on the machine checks for possible welding errors.

After production and control, the pipes are automatically cut with plasma to the desired length according to the customer's request, taking into account the relevant specifications and standard requirements. Mazlum Çelik Boru manufactures spiral pipes at a level that meets the requirements of national and international standards such as API, Gost-R, DIN, ASTM, BS, EN, UNI, and can produce with different materials from S235JR quality to API 5L X70M PSL2 quality.

Production is carried out according to;

- During surface preparation, ISO 8501-1, ISO 8501-2, and ISO 8501-3 standards
- For polyethylene coating; TS 5139, EN 10288, DIN 30670, UNI 9099, NFA 49710 AWWA C-215 standards
- For Polypropylene Coating, DIN 30678, NFA 49711 standards
- For polyurethane coating, AWWA C-222 , EN 10290 standards
- In Epoxy Coating; EN 10289, AWWA C-210, NFA 49709 standards.

Depending on production standards and customer requirements, weld seams are controlled by 100% ultrasonic and X-Ray film radiography methods. Spiral Welded Steel Pipes are subjected to 100% tightness test in hydrotest device, depending on the production standard.





Specifications

- High strength
- High impact and pressure resistance
- High carrying capacity
- Stabilility
- Long life
- Elasticity
- Formability
- Low maintanence cost
- Environment-friendly
- Cost-effective

Production Range Ø 219.1 mm - Ø 3810 mm (8 5/8" - 150")

Wall Thickness 4 mm - 28 mm (0.157" - 1.10")

Pipe Length 4 m - 16 m (Special production up to 46 m)

Product Information

> Product Name

Bare Spiral Welded Steel Pipes



Spiral welded steel pipe is the process of wrapping the flat sheet in the form of a spiral in the form of a pipe and joining the band edges from the inside and outside with the submerged arc welding method. Spiral pipes, which can be used for the transportation of many liquids such as water, wastewater, oil, natural gas, can also be used as pile pipes in constructions and as the foot of many heavy metals such as advertising signboards, billboards and totems.

Internal and External Welding

Immediately after the pipe forming process, inside welding is carried out around 30 mm behind the edge contact point by submerged arc welding process. Followed by half helical turn which depending on machine design external welding is carried out depending on pipe diameter and wall thickness; in addition to the individual and relative. All the welding parameters (Current, voltage, speed and etc.) and welding consumables are specified in Welding Procedure Specifications.

Ultrasonic Inspection

The produced pipes are control and record by Automatic On-Line Ultrasonic Control and computer systems. The faultless pipe production is realized by applying advanced ultrasonic evaluation system and program. The produced pipes are performing body and HAZ lamination and weld seam testing.

The length cutting shall be carried out by plasma cutting method according to customer specification.

Usage Areas of Steel Pipes

In parallel with the technological developments, spiral welded steel pipes, which have gained even longer life thanks to corrosion protection techniques and materials, take the first place in the fields of use thanks to the features stated below.

Usage Areas

- Water Distribution Lines
- Petroleum Pipelines
- Natural Gas Pipes
- Foundation Piles
- Industrial Pipe Network
- Steel Structures
- Compressed Air Line Pipes
- Drilling Wells
- Transportation of High Temperature Water
- Shipyard and Harbor Pile

> Technical Specifications

Production Standards	Steel Grades
API 5L	L175/A25, L175P/A25P, L210/A, L245/B, L290/X42, L320/X46, L390/X56, L415/X60, L450/X65, L485/X70, L245R/BR, L290R/X42R, L320N/X46N, L360N/X42N, L390N/X56N, L245N/BN, L290N/X42N, L320Q/X46Q, L360Q/X52Q, L390Q/X56Q, L245Q/BQ, L290Q/X42Q, L320M/X46M, L360M/X52M, L390M/X56M, L245M/BM, L290M/X42M, L415N/X60N, L450Q/X65Q, L485Q/Z70Q, L415Q/X60Q, L450M/X65M, L485M/X70M, L415M/X60M
EN 10217-1	P195TR1-P195TR2, P235TR1-P235TR2, P265TR1-P265TR2, S235JR, S275JR
EN 10219-1	S235JRH, S275J0H, S275J2H, S275NH, S275NLH, S355JOH, S355J2H, S355K2H, S355NH, S355NLH, S460NH, S460NLH, S420, S460, X60, X65, X70
AWWA C200	ASTM A-570, ASTM A-36, ASTM A-283
ASTM A53	Grade A, Grade B
ASTM A252	Grade 1, Grade 2, Grade 3
ISO 3183	L175/A25, L175P/A25P, L210/A, L245/B, L290/X42, L320/X46, L390/X56, L415/X60, L450/X65, L485/X70, L245R/BR, L290R/X42R, L320N/X46N, L360N/X42N, L390N/X56N, L245N/BN, L290N/X42N, L320Q/X46Q, L360Q/X52Q, L390Q/X56Q, L245Q/BQ, L290Q/X42Q, L320M/X46M, L360M/X52M, L390M/X56M, L245M/BM, L290M/X42M, L415N/X60N, L450Q/X65Q, L485Q/Z70Q, L415Q/X60Q, L450M/X65M, L485M/X70M, L415M/X60M
EN 10208-2	L245MB, L290MB, L360MB, L415MB
EN 10224	L235, L275, L355
EN 1090-2	L175/A25, L175P/A25P, L210/A, L245/B, L290/X42, L320/X46, L390/X56, L415/X60, L450/X65, L485/X70, L245R/BR, L290R/X42R, L320N/X46N, L360N/X42N, L390N/X56N, L245N/BN, L290N/X42N, L320Q/X46Q, L360Q/X52Q, L390Q/X56Q, L245Q/BQ, L290Q/X42Q, L320M/X46M, L360M/X52M, L390M/X56M, L245M/BM, L290M/X42M, L415N/X60N, L450Q/X65Q, L485Q/Z70Q, L415Q/X60Q, L450M/X65M, L485M/X70M, L415M/X60M, S235JRH, S275J0H, S275J2H, S275NLH, S275NLH, S355J0H, S355J2H, S355K2H, S355NLH, S355NLH, S460NLH, S420, S460

LCA Information

Declared unit

1 tonne (1000kg) of fabricated steel product manufactured in Adana facility (TR).

Reference service life

Not applicable

10

Time representatives

The production data in this LCA study represents the period of 1st January 2020 and 31st December 2020.

Database(s) and LCA software used

Simpro v9.2 and Ecoinvent v3.7.

Description of system boundaries

Cradle to gate (A1-3) with options, modules C1-C4, module D.

Data quality and data collection

According to EN 15804:2012+A2:2019 specific data was used for module A3 (Processes the manufacturer has influence over) and was gathered from Mazlum Boru Adana plant. Specific data includes actual product weights, amounts of raw materials used, product content, energy consumption, transport figures, water consumption and amounts of wastes. For A1 and A2 modules, according to EN 15804:2012+A2:2019, generic data was applied and was obtained from Ecoinvent v3.7.

Allocation

Mass allocation has been applied for preconsumer recycled materials according to EN 15804:2012+A2:2019.

Cut-off rules

Life Cycle Inventory data for a minimum of 99% of total inflows to the three life cycle stages have been included and a cut-off rule of 1% regarding energy, mass and environmental relevance was applied. Impacts caused by treatment operations have been calculated lower than 1% environmental relevance.

Modules declared, geographical scope, share of specific data (in GWP-GHG indicator) and data variation

	Pr	oduct Sta	ge	Constr Proc Sta	uction ess ge			I	Use Stage	1				End OF Life StageLife Stag			Resource Recovery Stage
	Raw material supply	Transport	Manufacturing	Transport from the gate to the site	Assembly	Use	Maintanence	Repair	Replacement	Refurbishment	Operaitional energy use	Operational water use	De-construction	Transport	Waste processing	Disposal	Reuse - Recovery - Recycling Potential
MODULES	A1	A2	A3	A4	A5	B1	B2	B3	B4	B5	B6	B7	C1	C2	С3	C4	D
Module declared	х	х	х	ND	ND	ND	ND	ND	ND	ND	ND	ND	х	х	х	х	х
Geography	TR	TR	TR	-	-	-	-	-	-	-	-	-	GLO	GLO	GLO	GLO	GLO
Specific data used		>99.5%		-	-	-	-	-	-	-	-	-	-	-	-	-	-
Variation- products	No	ot Releva	int	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Variation-sites	No	ot Releva	int	-	-	-	-	-	-	-	-	-	-	-	-	-	-

X = Declared; ND = Not Declared

» System Diagram



> Description of Declared Modules

A1 - Raw Materials Supply

This stage takes into account raw material extraction, processing and energy used in the production process.

A2 - Transport to the Manufacturer

This stages include transportation of the raw materials from supplier to factory gate. Transportation types are considered as seaway, road, railroad, etc.

A3 - Manufacturing

This stage includes energy and water consumption during the manufacturing process. Additionally, packaging materials are covered by this stage. Followed production processes are as;

- Spiral Welding
- Coating

12

C1 - De-construction

The dismantling of steel pipe has a very low impact considering the impact throughout the life of the installation. It is assumed that, in C1 module, same electricity and diesel is consumed as during the construction installation of steel pipe.

C2 - Transport to Waste Processing

An average distance of 100km has been assumed for the transport to recycling facility. Transport is calculated on the basis of a scenario with the parameters described in the table below.

Parameters	C2 Module
Transport by road*	Lorry >32 metric ton
Distance (km)	100
Database	Ecoinvent v3.7

*Technology is euro 5

C3 - Waste Processing for Reuse, Recovery and/or Recycling

The material and energy expenses required for Module C3 are negligible. It is assumed that there is no sorting or processing required for steel pipes.

C4 - Final Disposal

100% of used product after the lifetime will be collected and recycled into the manufacturing system. It is assumed that 5% of the product is lost during deconstruction and 95% is reached to recycling system. The recycling rate of steel products is assumed to be 95% based on Annex C of the Product Environmental Footprint Guidance of European Commission.

D - Reuse, Recovery or Recycling Potential

Scrap inputs to the production stage are substracted from scrap to be recycled at end of life in order to obtain the net scrap output from the product system. This remaining net scrap is then delivered to recycling process. Module D reports the environmental aspects of recycled scrap generated at the end of life minus that used at the production stage.

Information on Which Life Cycle Stages Are Not Considered

This EPD only covers the Cradle to Gate A1-3, C1-4 and D stages because other stages are very dependent on particular scenarios and are better developed for specific building or construction works.



> Content Declaration

Content declaration of 1000kg of Bare Spiral Welded Steel Pipes					
Material	Share				
Hot rolled steel coil	100%				
Renewable material	0%				
Biogenic carbon	0%				

Environmental Performance

Potential Environmental Impact Mandatory Indicators According to EN 15804

		Results f	or 1000kg of Bare	Spiral Welded Stee	el Pipes		
Indicator	Unit	A1:A3	C1	C2	C3	C4	D
GWP-fossil	kg CO ₂ eq	1750	1.36	9.05	0	0.271	-984
GWP-biogenic	kg CO ₂ eq	11.3	0.033	0.019	0	0.001	-7.89
GWP-luluc	kg CO ₂ eq	2.31	0.002	0.003	0	7.37E-05	-0.883
GWP-total	kg CO ₂ eq	1763	1.39	9.07	0	0.272	-993
ODP	kg CFC 11eq	1.12E-04	7.66E-08	2.13E-06	0	1.12E-07	-6.08E-05
АР	mol H+ eq	8.31	0.007	0.037	0	0.003	-4.60
ED-Ereshwater	kg PO43- eq	1.13	0.001	0.005	0	3.44E-04	-0.639
LFFITESIIWater	kg P eq	0.106	9.89E-05	6.50E-05	0	2.86E-06	-0.058
EP-Marine	kg N eq	2.03	0.001	0.011	0	8.89E-04	-1.16
EP-Terrestrial	kg N eq	18.3	0.013	0.126	0	0.010	-10.3
РОСР	kg NMVOC eq	7.38	4.78E-03	0.041	0	0.003	-4.25
ADP-minerals & metals*	kg Sb eq	0.013	9.81E-06	2.12E-05	0	6.07E-07	-8.04E-03
ADP-fossil*	MJ	20892	20.1	141	0	7.60	-11721
WDP	m ³	854	1.06	0.466	0	0.342	-500

GWP-fossil = Global Warming Potential fossil fuels; **GWP-biogenic** = Global Warming Potential biogenic; **GWP-luluc** = Global Warming Potential land use and land use change; **ODP** = Depletion potential of the stratospheric ozone layer; **AP** = Acidification potential, Accumulated Exceedance;

EP-freshwater = Eutrophication potential, fraction of nutrients reaching freshwater end compartment; **EP-marine** = Eutrophication potential, fraction of nutrients reaching marine end compartment; **EP-terrestrial** = Eutrophication potential, Accumulated Exceedance; **POCP** = Formation potential of tropospheric ozone; **ADP-minerals&metals** = Abiotic depletion potential for non-fossil resources; **ADP-fossil** = Abiotic depletion for fossil resources potential; **WDP** = Water (user) deprivation potential, deprivation-weighted water consumption

* Disclaimer: The results of this environmental impact indicator shall be used with care as the uncertainties of these results are high or as there is limited experience with the indicator.

Potential Environmental In	pact Additional Mandato	ry and Voluntary Indicators
-----------------------------------	-------------------------	-----------------------------

	Results for according to PCR2019:14 for 1000kg of Bare Spiral Welded Steel Pipes											
Indicator	Unit	A1:A3	C1	C2	C3	C4	D					
GWP-GHG ¹	kg CO ₂ eq	1694	1.30	8.97	0	0.267	-952					
Results for according to EN 15804+A2 for 1000kg of Bare Spiral Welded Steel Pipes												
РМ	[disease inc]	1.38E-04	4.13E-07	8.15E-07	0	5.01E-08	-8.11E-05					
IRP	[kBq U235 eq]	67.0	0.117	0.619	0	0.031	-39.3					
ET-freshwater	[CTUe]	49562	32.7	108	0	4.78	-29556					
HT-cancer	[CTUh]	2.62E-05	3.79E-08	3.35E-09	0	1.42E-10	-1.61E-05					
HT-non-cancer	[CTUh]	5.02E-05	3.37E-08	1.17E-07	0	2.98E-09	-3.01E-05					
SQP	[pt]	7976	5.10	162	0	16.0	-4305					

GWP-GHG = Global Warming Potential total excl. biogenic carbon following IPCC AR5 methodology; **IRP** = Ionizing radiation, human health;

cronyms **ET-freshwater =** *Eco-toxicity (freshwater)*; **HT-cancer =** *Human toxicity, cancer effects*; **HT-non-cancer =** *Human toxicity, non-cancer effects*; **SQP** = Potential soil quality index (SQP)



1 The indicator includes all greenhouse gases included in GWP-total but excludes biogenic carbon dioxide uptake and emissions and biogenic carbon stored in the product. This indicator is thus equal to the GWP indicator originally defined in EN 15804:2012+A1:2013.

> Use of Resources

		Results fo	or 1000kg of Bare	Spiral Welded Stee	el Pipes		
Indicator	Unit	A1:A3	C1	C2	C3	C4	D
PERE	MJ	1850	2.35	1.72	0	0.061	-966
PERM	MJ	0	0	0	0	0	0
PERT	MJ	1850	2.35	1.72	0	0.061	-966
PENRE	MJ	22195	21.2	150	0	8.07	-12427
PENRM	MJ	0	0	0	0	0	0
PENRT	MJ	22195	21.2	150	0	8.07	-12427
SM	kg	1047	0	0	0	0	0
RSF	MJ	0	0	0	0	0	0
NRSF	MJ	0	0	0	0	0	0
FW	m ³	83.8	0.166	0.109	0	0.011	-46.7

PERE = Use of renewable primary energy excluding renewable primary energy resources used as raw materials; **PERM** = Use of renewable primary

energy resources used as raw materials; **PERT** = Total use of renewable primary energy resources; **PENRE** = Use of non-renewable primary energy

Acronyms excluding non-renewable primary energy resources used as raw materials; **PENRM** = Use of non-renewable primary energy resources used as raw materials; **PENRT** = Total use of non-renewable primary energy resources; **SM** = Use of secondary material; **RSF** = Use of renewable secondary fuels; **NRSF** = Use of non-renewable secondary fuels; **FW** = Use of net fresh water



Waste Production

Results for 1000kg of Bare Spiral Welded Steel Pipes										
Indicator	Unit	A1:A3	C1	C2	C3	C4	D			
Hazardous waste disposed	kg	36.0	0	0	0	0	0			
Non-hazardous waste disposed	kg	0.293	0	0	0	50.0	0			
Radioactive waste disposed	kg	0	0	0	0	0	0			

> Output Flows

	Results for 1000kg of Bare Spiral Welded Steel Pipes										
Indicator	Unit	A1:A3	C1	C2	C3	C4	D				
Component for re-use	kg	0	0	0	0	0	0				
Materials for recycling	kg	0	0	0	0	950	0				
Materials for energy recycling	kg	0	0	0	0	0	0				
Exported energy, electricity	MJ	0	0	0	0	0	0				
Radioactive waste disposed	MJ	0	0	0	0	0	0				





References

» ISO 14020:2000

Environmental labels and declarations -- General principles

» ISO 14040:2006

Environmental management -- Life cycle assessment -- Principles and framework

» ISO 14044:2006

Environmental management -- Life cycle assessment -- Requirements and guidelines

» ISO 14025:2006

Environmental labels and declarations -- Type III environmental declarations -- Principles and procedures

EN 15804:2012+A2:2019

Sustainability of construction works - Environmental product declarations - Core rules for the product category of construction product

- The International EPD® System www.environdec.com
- > The International EPD® System The General Programme Instructions v3.01
- > The International EPD® System PCR 2029:14 Construction products v1.1 (EN 15804:A2)
- Ecoinvent 3.7 www.ecoinvent.org
- SimaPro LCA Software www.simapro.com
- Mazlum Spiral Pipes www.mazlumboru.com.tr



Contact

Third party verfier Vladimír Kočí, PhD

Vladimír Kočí, PhD Šárecká 5, 16000 Prague 6/Czech Republic *www.lcastudio.cz*

Owner of Declaration

Mazlum Mangatay Boru Sondajcılık İnş. Tarım Ürünleri San. Tic. A.Ş. Adana Hacı Sabancı OSB İstiklal Cd. No:10 Sarıçam/Adana www.mazlumboru.com.tr

LCA Study & EDP Design Conducted By

Semtrio Sustainability Consulting BUDOTEK Teknopark, No 8/27 Umraniye/Istanbul Turkey www.semtrio.com







19 I



Adana Hacı Sabancı OSB İstiklal Cd. No:10 Sarıçam/Adana www.mazlumboru.com.tr